


**MAYPRENE® MW666**  
**Polypropylene ( PP )**

Physical Properties	Method	Testing Condition	Unit	Typical Value
Specific Gravity	ASTM D-792	-	g/cm <sup>3</sup>	0.9
Water Absorption	ASTM D-570	23 °C	%	0.02

**Mechanical Properties**

Tensile Strength	ASTM D 638	-	kg/cm <sup>2</sup>	300
Tensile Elongation	ASTM D 638	-	%	150
Flexural Modulus	ASTM D 790	-	kg/cm <sup>2</sup>	12000
Flexural Strength	ASTM D 790	-	kg/cm <sup>2</sup>	400
Izod Impact	ASTM D 256	V-notched, 1/8"	kg.cm/cm	10
Anti-Oxidant Content	-	-	%	0.1
UV Stabilizer	-	-	%	0.1

**Thermal Properties**

Melt Flow Index	ASTM D 1238	-	g/10min	8
Heat Distortion Temperature	ASTM D-648	18.6kg/cm <sup>2</sup>	°C	90
Flammability	UL-94	-	-	HB

**Processing Properties**

Drying Hour	-	-	Hr	2
Drying Temperature	-	-	°C	80
Melt Temperature	-	-	°C	190-200

All information is furnished in good faith, without warranty, representation, inducement or a license of any kind. No guarantee is given that Metro Wealth Polymer products will be suitable in purchasers' formulations or processes for any particular end use.