

METRO WEALTH POLYMER SDN. BHD	DATASHEET	
JAN 01,2008		

MAYREX® MW111
Acrylonitrile-Butadiene-Styrene (ABS)

Physical Properties	Method	Testing Condition	Unit	Typical Value
Specific Gravity	ASTM D-792	-	g/cm ³	1.05
Water Absorption	ASTM D-570	23 °C	%	0.30

Mechanical Properties

Tensile Strength	ASTM D 638	-	kg/cm ²	510
Tensile Elongation	ASTM D 638	-	%	15
Flexural Modulus	ASTM D 790	-	kg/cm ²	25000
Flexural Strength	ASTM D 790	-	kg/cm ²	780
Izod Impact	ASTM D 256	V-notched, 1/8"	kg.cm/cm	15

Thermal Properties

Melt Flow Index	ASTM D 1238	-	g/10min	7
Heat Distortion Temperature	ASTM D-648	18.6kg/cm ²	°C	92
Flammability	UL-94	-	-	HB

Processing Properties

Drying Hour	-	-	Hr	3-4
Drying Temperature	-	-	°C	85
Melt Temperature	-	-	°C	200-240

All information is furnished in good faith, without warranty, representation, inducement or a license of any kind. No guarantee is given that Metro Wealth Polymer products will be suitable in purchasers' formulations or processes for any particular end use.