

MAYRON® MW3620 U**Polycarbonate 20% Glass Reinforced (PC 20% GF)****Metro Wealth Under UL Register File No: (E 306925)**

Physical Properties	Method	Testing Condition	Unit	Typical Value
Specific Gravity	ASTM D-792	-	g/cm ³	1.35
Water Absorption	ASTM D-570	23 °C	%	0.29

Mechanical Properties

Tensile Strength	ASTM D 638	-	kg/cm ²	660-815
Tensile Elongation	ASTM D 638	-	%	2-5
Flexural Modulus	ASTM D 790	-	kg/cm ²	37000-50000
Flexural Strength	ASTM D 790	-	kg/cm ²	950-1350
Izod Impact	ASTM D 256	V-notched, 1/8"	kg.cm/cm	6-8

Thermal Properties

Melt Flow Index	ASTM D 1238	-	g/10min	6-10
Heat Distortion Temperature	ASTM D-648	4.6kg/cm ²	°C	121.4 – 127.4
Flammability	UL-94	-	-	V0

Processing Properties

Drying Hour	-	-	Hr	3-4
Drying Temperature	-	-	°C	120
Melt Temperature	-	-	°C	270-290

All information is furnished in good faith, without warranty, representation, inducement or a license of any kind. No guarantee is given that Metro Wealth Polymer products will be suitable in purchasers' formulations or processes for any particular end use.