

MAYRYL®MW820 U**Polypropylene Oxide 20% Glass Reinforced (PPO 20% GF)****Metro Wealth Under UL Register File No: (E 306925)**

Physical Properties	Method	Testing Condition	Unit	Typical Value
Specific Gravity	ASTM D-792	-	g/cm ³	1.20
Water Absorption	ASTM D-570	23 °C	%	0.05

Mechanical Properties

Tensile Strength	ASTM D 638	-	kg/cm ²	480 - 650
Tensile Elongation	ASTM D 638	-	%	2 - 3
Flexural Modulus	ASTM D 790	-	kg/cm ²	37000 - 50000
Flexural Strength	ASTM D 790	-	kg/cm ²	820 - 1100
Izod Impact	ASTM D 256	V-notched, 1/8"	kg.cm/cm	6 - 9

Thermal Properties

Melt Flow Index	ASTM D 1238	-	g/10min	1 - 2
Heat Distortion Temperature	ASTM D-648	4.6kg/cm ²	°C	118 - 124
Flammability	UL-94	-	-	HB

Processing Properties

Drying Hour	-	-	Hr	90 - 100
Drying Temperature	-	-	°C	2 - 4
Melt Temperature	-	-	°C	260 - 280

All information is furnished in good faith, without warranty, representation, inducement or a license of any kind. No guarantee is given that Metro Wealth Polymer products will be suitable in purchasers' formulations or processes for any particular end use.